

Toolox[®] 40

General Product Description

The pre-hardened, exceptionally clean engineering and tool steel.

Toolox[®] 40 is a pre-hardened steel suitable for engineering components and mold applications. It possesses good dimensional stability after machining.

Toolox[®] 40 features the same machinability as the conventional P20/W.Nr 1.2311 steel, despite its nearly 100 HBW higher nominal hardness, in combination with the renowned high dimensional stability of Toolox[®]. This makes Toolox[®] 40 your ideal choice in engineering components that require higher strength, or in molds and dies that demand higher wear resistance.

Dimension Range

Toolox[®] 40 is available as plates in thicknesses between 6.0 - 130.0 mm. Other dimensions can be available on request.

Mechanical Properties

Thickness (mm)	Hardness ¹⁾ (HBW)
6.0 - 130.0	360 - 420

¹⁾ Hardness is measured, according to EN ISO 6506-1, on a milled surface 0.5 - 2 mm below the plate surface.

Impact Properties

Thickness (mm)	Min impact energy for transversal testing, Charpy V 10x10 mm test specimen ¹⁾
6.0 - 130.0	20 J / 20 °C

¹⁾ Impact testing according to EN 10 025, EN ISO 148 with a 2 mm striker.

Ultrasonic testing

Ultrasonic inspection is carried out according to : EN 10 160 with extra demands according to specification SSAB V6.

Tolerances

More details are given in SSAB's brochure Toolox® Guarantees and on www.toolox.com.

Thickness

Tolerances according to Toolox® Thickness Guarantee.

Toolox® Guarantees meets the requirements of EN 10029 Class C but offers more narrow tolerances.

Length and Width

Tolerances according to EN 10029.

Flatness

Tolerances are according to Toolox® Flatness Guarantees, which are more restrictive than EN 10029 Class N (steel type L).

Surface Properties

According to EN 10163-2 Class B Subclass 3.

Delivery Conditions

Quenched and Tempered at a minimum temperature of 590 °C.

On delivery from SSAB the plates meet the following specifications:

- Free from mill scale
- Not repair welded

Delivery requirements can be found in SSAB's brochure Toolox® Guarantees or at www.toolox.com.

Fabrication and Other Recommendations

Toolox® products is not intended for further heat treatment. If Toolox is heated above 590 °C after delivery from SSAB no guarantees for the properties of the steel are given. Nitriding or surface coating may be carried out if the temperature is below 590 °C.

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on the product. Grinding, especially of primer coated plates, may produce dust with high particle concentration.

Welding, bending and machining

For information concerning welding and fabrication, see SSAB's brochures on www.ssab.com or consult Tech Support.

Contact Information

www.ssab.com/contact