

durostat 400/450/500/B2

Wear-resistant steels with best workability

The steel grades durostat 400, durostat 450 and durostat 500 are wear-resistant special steels with hardness of approx. 400 HB, 450 HB resp. 500 HB. These steels provide high levels of resistance to mechanical wear and are specially suitable for components exposed to heavy abrasion, e.g. loading devices, shovels of wheel loaders, bodies of trough tipping wagons, conveyors, excavator components, road machines, screens and crushers. The high hardness is reached by accelerated cooling directly after hot rolling (direct quenching) or by conventional quenching in a water quench. Direct quenching is mainly applied due to improved toughness and reduced scale. State-of-the-art alloying concepts with low carbon content provide good weldability.

durostat B2 steels are delivered in as-rolled condition (non-quenched). The highest achievable hardness is approximately 500 HB. These steel grades are used in components of agricultural machinery, cutting edges for front-end loaders and brick-molding boxes.

Convincing advantages

- » Longer service life with much higher resistance to wear
- » Weight savings due to reduced plate thickness as a result of high hardness
- » Good surface quality due to thinner, more easily removable rolling scale
- » Good weldability with elimination of preheating for small plate thicknesses
- » Guaranteed toughness for low temperature applications

Chemical composition

Heat analysis in mass %

durostat®	C max.	Si max.	Mn max.	P max.	S max.	Al min.	Cr max.	Mo max.	B max.	Ti max.
400	0.18	0.60	2.10	0.025	0.010	0.020	1.00	0.50	0.005	0.050
450	0.23	0.60	2.10	0.025	0.010	0.020	1.00	0.50	0.005	0.050
500	0.30	0.60	2.10	0.025	0.010	0.020	1.00	0.50	0.005	0.050
B2	0.30	0.60	2.10	0.025	0.010	0.020	1.00	0.50	0.005	0.050

The steel is fine grain melted and may contain microalloying elements such as Nb and V.

Carbon equivalent

durostat®	Plate thickness [mm]	Mass percentages [%]	
		CEV ¹⁾ max.	CET ²⁾ max.
400	5 ≤ 35	0.52	0.35
	> 35 - 120	0.57	0.37
450	5 ≤ 15	0.57	0.37
	> 15 - 70	0.59	0.39
500	8 ≤ 30	0.59	0.44
	> 30 - 50	0.67	0.47

¹⁾ CEV = C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15, according to IIW

²⁾ CET = C + (Mn + Mo)/10 + (Cr + Cu)/20 + Ni/40, according to SEW 088

Mechanical properties: Hardness/Tensile strength

durostat®	Hardness [HB]	Standard values ¹⁾			
		Hardness [HB]	Yield strength R _{0.2H} [MPa]	Tensile strength R _m [MPa]	Fracture elongation A ₅ [%]
400	360 - 440	400	1,000	1,250	10
450	410 - 490	450	1,100	1,400	9
500	460 - 540	500	1,200	1,550	8
B2	ca. 500 ²⁾	200	400	650	20

¹⁾ Typical values for plate thickness of 20 mm

²⁾ As-delivered condition is non-quenched; achievable hardness after water quenching

Mechanical properties: Notch impact energy/Edging radii

durostat®	Plate thickness [mm]	Notch impact energy ¹⁾ Av [Joule] min. -40 °C	Edging radii Ri min. at 90° edging (s = plate thickness) Position of the bending edge to the rolling direction	
			Longitudinal	Transverse
Guaranteed values				
400	5 - 50	27	-	-
	> 50 ≤ 120	upon request	-	-
450	5 - 50	20	-	-
500	8 - 50	upon request	-	-
Standard values ²⁾				
400	-	50	4 s	3 s
450	-	30	5 s	4 s
500	-	20	5 s	4 s

¹⁾Notch impact bending test in accordance with EN ISO 148-1 on Charpy-V longitudinal samples at -40 °C. The mean value from 3 individual samples must reach the specified requirements. No individual value may be below 70% of the guaranteed mean value. For thicknesses < 12 mm, subsize-specimen with dimensions of 10 x 7.5 mm or 10 x 5 mm are tested. The guaranteed value is reduced in proportion to the sample cross-section.

²⁾Typical values of notch impact energy for plate thickness of 20 mm

Available dimensions

Maximum width per thickness; minimum width 1,500 mm; for thickness of 5 mm the minimum width is 2,000 mm

durostat®	Plate thickness [mm]	Max. width [mm]	Max. length [mm]	As-delivered condition ⁵⁾
400	5 ≤ 12	2,500	12,000 (8,000 for thickness 5 mm and a width ≥ 2,000 mm)	direct quenched
	> 12 ≤ 120	3,000		
450	5 ≤ 12	2,500		
	> 12 ≤ 70	3,000		quenched or direct quenched
500	8 ≤ 50	2,500	18,700	non-quenched
B2	8 ≤ 50	2,500		

Weight per plate is max. 16 t.
Additional dimensions upon request.

The information and product properties contained in this printed material are non-binding and serve the sole purpose of technical orientation. They do not replace individual advisory services provided by our sales and customer service teams. The product information and characteristics set forth herein shall not be considered as guaranteed properties unless explicitly stipulated in a separate contractual agreement. For this reason, voestalpine shall not grant any warranty nor be held liable for properties and/or specifications other than those subject to explicit agreement. This also applies to the suitability and applicability of products for certain applications as well as to the further processing of materials into final products. All application risks and suitability risks shall be borne by the customer. The General Terms of Sale for Goods and Services of the voestalpine Steel Division shall apply to all materials supplied by the voestalpine Steel Division and can be accessed using the following link: www.voestalpine.com/stahl/en/The-Steel-Division/General-Terms-of-Sale

Technical changes are reserved. Errors and misprints are excepted. No part of this publication may be reprinted without explicit written permission by voestalpine Stahl GmbH.

Please find further information and downloadable files at www.voestalpine.com/durostat/en

